


WWW.GELEST.COM acrylates@gelest.com

BIMAX® DMA

N,N-Dimethylacrylamide CAS No. 2680-03-7 EINECS No. 2202375



Applications

This material is a high purity monomer for contact lens applications.

Typical Properties

Purity, % Color, APHA Moisture, % MEHQ, ppm > 99.5 < 20 < 0.2 500

Physical Properties

Appearance Molecular weight Density (relative), 25°C Flash Point, closed cup Boiling range, 20 mmHg Water solubility, 20°C

clear, colorless liquid 99.1 g/mol 0.962 g/cm³ 70°C 80-81°C 1000 g/L

Packaging

1-gallon bottles, containing 3 kg each 5-gallon poly pails, containing 15 kg each

Storage and Handling

Store at temperatures below 32°C, away from heat, sunlight, and ignition sources. Saturate with atmospheric oxygen. Wear goggles and gloves. Eye and skin contact, as well as inhalation, should be avoided. If contact occurs, wash affected area immediately with cold water. Consult the Safety Data Sheet.

This information is presented for your consideration in the belief that it is accurate and reliable; however, Bimax makes no guarantees or warranty, either expressed or implied, of the accuracy or the completeness of this information. The information in this data sheet is designed only as a guidance for safe handling, storage and use of the substance. It is not a specification, nor does it guarantee any specific properties. All chemicals should be handled only by competent personnel, within a controlled environment. Individuals receiving this information are expected to use their own judgment in determining the relevancy for a particular circumstance. Accordingly, Bimax will not be responsible for damages of any kind resulting from the use of, or reliance upon, such information.

281 Industrial Road Glen Rock, Pennsylvania 17327, USA Tel: +1 717-227-1774 Fax: +1 717-227-1775